



# Sales Specification

---

Product: **EPOLENE® N-21 Polymer**

**Specification: N-21**  
**Effective Date: 1-Oct-2012**  
**Version: 7**  
**Pages: 1 of 1**

---

## **A. GENERAL**

- A-1 This specification replaces Sales Specification N-21 Version 6, dated February 2006. This revision reflects updated analytical methods.
- A-2 This specification describes a grade of *EPOLENE* Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

## **B. PROPERTIES AND TEST METHODS**

	<b><u>Property</u></b>	<b><u>Specification Limits</u></b>	<b><u>Test Method</u></b>
B-1	Mettler Softening Point, °C	115.0 - 123.0	ASTM D6090
B-2	Viscosity @ 150C, CPS	250 - 450	ASTM D3236
B-3	Yellowness Index	18 MAX	ASTM D6290

---

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.